

Diablillos Phase 1 Drilling - Summary of Highlighted Intercepts

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t
19-001	166	231	Oxides	65	105	0.2	-	120	1.6
19-002	137.5	155	Oxides	17.5	604	0.1	-	612	8.2
	242	257	Oxides	15	286	10.4	-	1,066	14.2
	367	376	Sulphides	9	49	7.3	1.28	729	9.72
20-001	261	290	Mixed	29	430	4.3	2.77	1,037	13.8
	including 261	275	Transition	14	197	6.4	2.53	937	12.5
	including 275	290	Sulphides	15	658	2.4	5.10	1,363	18.2
20-002	337	349	Sulphides	12	13	1.1	2.56	362	4.8
20-003	70	87	Oxides	17	21	2.3	-	195	2.6
	267	289	Oxides	22	25	4.2	-	342	4.6
	405	407	Sulphides	2	28	3.3	4.49	741	9.9
20-004	276	286	Oxides	10	28	1.4	-	133	1.8
20-005	25.5	36	Oxides	10.5	26	1.7	-	152	2.0
	179	184	Oxides	5	192	0.1	-	202	2.7
20-006	206	249	Oxides	43	64	0.7	-	119	1.6
	259	284	Oxides	25	44	1.5	-	153	2.0
	267	275	Oxides	8	44	3.1	-	280	3.7
	including 273	275	Oxides	2	56	9.5	-	765	10.2
20-007	157	218	Oxides	61	256	0.3	-	275	3.7
	including 178	206	Oxides	28	383	0.3	-	409	5.5
	260	262	Sulphides	2	28	23.4	-	1,783	23.8
20-008	352	360	Sulphides	8	-	1.7	2.01	331	4.4
20-009	171	254	Oxides	83	289	1.5	-	398	5.3
	275	280	Oxides	5	99	4.2	-	411	5.5
	287	289	Sulphides	2	55	5.3	2.04	662	8.8
20-010A	149.5	176.5	Oxides	27	167	-	-	167	2.2
	210	257	Oxides	47	96	3.4	-	349	4.7
	261	276	Sulphides	15	296	2.2	-	458	6.1
	316.5	320.5	Sulphides	4	30	4.1	1.52	497	6.6
20-012	150.5	176	Oxides	25.5	33	1.0	-	110	1.5
	183.5	185	Oxides	1.5	154	3.5	-	414	5.5
20-013	291.5	307	Oxides	15.5	14	1.9	-	153	2.0
	438	451	Sulphides	13	8	0.5	0.86	136	1.8

May 03, 2021

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t
including	441	447	Sulphides	6	23	0.9	1.34	226	3.0
20-015	92	101.5	Oxides	9.5	68	1.1	-	151	2.0
20-017	13	74	Oxides	61	105	1.1	-	190	2.5
including	42	55	Oxides	13	142	2.0	-	294	3.9
20-018	6	22.5	Oxides	16.5	114	1.1	-	198	2.6
including	6	12	Oxides	6	233	2.9	-	450	6.0
20-019	147.5	171.5	Sulphides	24	35	0.2	1.49	205	2.7
20-020	3	24	Oxides	21	132	2.9	-	352	4.7
including	3	16.5	Oxides	13.5	179	4.5	-	515	6.9
20-022	9.5	23	Oxides	13.5	31	2.9	-	251	3.3
20-024	83	110	Oxides	27	86	0.5	-	126	1.7
including	104	110	Oxides	6	168	0.2	-	179	2.4
20-025	58	64.5	Oxides	6.5	226	-	-	226	3.0
	83	105.5	Oxides	22.5	49	0.6	-	91	1.2
	143.3	154.5	Oxides	11.2	222	-	0.06	228	3.0
20-026	130	195	Oxides	65	151	1.9	-	292	3.9
Including	162	189	Oxides	27	208	4.3	-	530	7.1
Including	175	189	Oxides	14	236	6.7	-	741	9.9
20-027	141	244	Oxides	103	389	1.7	-	516	6.9
Including	141	163	Oxides	22	413	0.1	-	424	5.7
Including	163	180	Oxides	17	1,467	0.6	-	1,508	20.1
Including	166	168	Oxides	2	5,796	0.9	-	5,867	78.2
Including	181	244	Oxides	63	95	2.6	-	287	3.8
Including	190	244	Oxides	54	103	2.8	-	316	4.2
Including	231	238	Oxides	7	132	5.4	-	533	7.1
	250.5	256.6	Oxides	6	181	1.0	-	256	3.4
20-028	70	81	Oxides	11	89	1.2	-	177	2.4
	139	142	Oxides	3	37	5.5	-	451	6.0
Including	141	142	Oxides	1	66	12.8	-	1,026	13.7
20-030	205.5	218	Oxides	12.5	33	4.7	-	384	5.1
	260	264.5	Sulphides	4.5	11	3.2	-	270	3.6
20-032	56	73	Oxides	17	8	1.6	-	131	1.7
21-001	33	79	Oxides	46	70	0.8	-	133	1.8
21-002	132	147	Oxides	15	701	0.1	-	711	9.5
Including	132	142	Oxides	10	1,004	0.1	-	1,017	13.6

May 03, 2021

Hole	From (m)	To (m)	Type	Interval (m)	Ag g/t	Au g/t	Cu %	AgEq g/t	AuEq g/t	
	Including	132	134	Oxides	2	1,955	0.3	-	1,975	26.3
		219	271.8	Oxides	52.8	127	2.1	-	286	3.8
	Including	226	246	Oxides	20	185	3.2	-	424	5.7
21-003		106	142	Oxides	36	370	0.4	-	399	5.3
	Including	118	122	Oxides	4	635	0.6	-	677	9.0
	Including	132	137	Oxides	5	1,556	1.2	-	1,645	21.9
		207	252	Oxides	45	146	0.3	-	172	2.3
	Including	217	226	Oxides	9	233	1.1	-	318	4.2
21-004		142	159	Oxides	17	44	1.6	-	161	2.1
		184	192	Oxides	8	82	8.0	-	680	9.1
		239	245	Sulphides	6	63	4.4	0.7	463	6.2
	Including	243	245	Sulphides	2	143	11.2	1.3	1,116	14.9
21-005		58	77	Oxides	19	31	4.7	-	380	5.1
	Including	58	71	Oxides	13	34	6.4	-	517	6.9
		323.5	344	Sulphides	20.5	25	2.2	-	191	2.6
		327.5	336	Sulphides	8.5	33	4.0	-	334	4.5
		395	412	Sulphides	17	-	0.6	1.2	163	2.2
21-006		103	118	Oxides	15	80	0.1	-	89	1.2
21-007		91	127	Oxides	36	71	0.13	-	81	1.1
21-008		84	119	Oxides	35	39	1.0	-	116	1.6
	Including	84	96.5	Oxides	12	38	2.6	-	235	3.1
21-009		208	283	Oxides	75	167	2.2	-	335	4.5
	Including	225	263	Oxides	38	184	2.6	-	379	5.1
	Including	273	283	Oxides	10	111	6.3	-	586	7.8
	Including	274	280	Oxides	6	154	9.8	-	887	11.8
		312.4	314.4	Sulphides	2	24	5.3	1.7	593	7.9
21-010		208	210	Oxides	2	296	4.0	-	596	8.0
		241	260	Oxides	19	13	1.1	-	93	1.2

Notes

All results are rounded. Assays are uncut and undiluted. Intervals are drilled widths, not true widths. AgEq calculations for reported drill results are based on USD \$20.00/oz Ag, \$1,500/oz Au and \$3.00/lb Cu. The calculations assume 100% metallurgical recovery and are indicative of gross in-situ metal value at the indicated metal prices. The most recent technical report for the Diablillos Project is the 2018 Preliminary Economic Assessment (PEA) authored by Roscoe Postle Associates Inc. The PEA assumes average metallurgical recoveries of 82% Ag and 86% Au. No metallurgical testwork has yet been completed on the recovery of copper.